

1

#88

C O R P

PRESCRIBING THE RULES AND STANDARD SPECIFICATIONS
FOR STREET AND SIDEWALK WORK IN THE
TOWN OF SAN ANSELMO.

The Board of Trustees of the Town of San Anselmo do ordain
as follows:-

CONCRETE SIDEWALKS

Section 1. - The width of all concrete sidewalks shall be
determined by the Board of Trustees.

Section 2. - The thickness of all concrete sidewalks shall be
at least Three (3) inches after completion.

Prepare the surface of the ground wherever concrete
sidewalks are to be constructed, by excavating or filling to the
required depth or sub-grade, care being taken to ram or roll the
surface so prepared, so as to present a smooth and firm bearing to
receive the concrete.

The base or first layer of concrete shall have a thickness
for ramming or rolling of not less than Two and one-half (2-1/2)
inches, and shall be prepared and composed as follows:- To one (1)
part of best Portland cement there shall be Five (5) parts of clean
hard broken rock, ranging in size from one-half (1/2) inch to one
and one-half (1-1/2) inches in diameter, and two (2) parts of clean
sharp sand. The whole to be thoroughly mixed dry, water added, and
again thoroughly mixed ready for the work in hand. This mixture to
be immediately placed in position and rammed or rolled until the
water comes to the surface. Gravel conforming to the same mesh
composition may be substituted for rock.

The top or surface layer of concrete shall have a thickness
of one-half (1/2) inch, and shall be composed of equal parts of
best Portland cement and clean sharp sand, thoroughly mixed dry,
the proper amount of water added, and finished by a trowel to a
perfectly smooth surface, marked off in squares not exceeding two
and one-half (2-1/2) feet in any direction.

All concrete used in the work herein mentioned shall be
freshly mixed, and no concrete shall be used that has been rejected.

ROCK OR GRAVEL SIDEWALKS.

Section 3. - Rock or gravel sidewalks may be laid at the
discretion of the Board of Trustees. Rock or gravel used for said

2
C O N N E Y 33

purpose shall be of such dimension to pass a three-quarter (3/4) inch screen. Sidewalks of this class to have a thickness of two and one-half (2-1/2) inches.

The finished surface of all sidewalks shall conform to the lines and grades which shall be furnished by the Town Engineer, and the direction of the Board of Trustees of the Town of San Anselmo.

All work to be done to the entire satisfaction of the Town Engineer, or the Inspector duly appointed to act under him by the Board of Trustees.

All work shall be guaranteed against cracks or settlement for a period of one (1) year, and the Contractor will be required to furnish a bond for the same.

REDWOOD CURBS.

Section 4. - Redwood curbs are to be constructed of second black hard redwood planks not less than three (3) inches thick, and twelve (12) inches wide.

The curbing must be carefully set to the proper line and grade with earth or other material upon either side to hold it in place, well compacted.

ROCK GUTTERWAYS

Section 5. - The bottom of the excavation for rock gutterways is to be at least seven (7) inches below the surface of the finished gutterways.

The gutterways are to extend at least two (2) feet from the curbs, and are to be constructed of large flat stones having a thickness of not less than four (4) inches. These stones are to be laid with upper surfaces evened in such a way that the center of the gutterway will be depressed four (4) inches below its edge.

The center line of the gutterways is to be eight (8) inches below the required top of curb, except in cases where otherwise directed by the Board of Trustees.

The stones for the gutterways are to be laid on a bed of concrete three (3) inches thick, composed of one (1) part cement, two (2) parts sand, and five (5) parts fine broken rock.

The stones are to be placed by hand, being imbedded in the concrete while the same is still fresh. They are to be placed

(1) 7 2 1 0 8 0

closely and compactly, and the spaces between them are to be filled with spawls and grouted with a thin cement mortar, composed of one (1) part Portland cement to one (1) part of sand.

All rock for gutterways must be hard and durable, clean and free from clay and dirt.

Section 6. - Ordinance No. 86 of the Town of San Anselmo, passed and adopted June 14th, 1911, is hereby expressly repealed.

Section 7. - This Ordinance shall take effect and be in force immediately from and after its passage.

Passed and adopted this 9th day of August 1911, by the following vote:-

Ayes:- Trustees Gagan, Schuader, Whitaker, Stratford & Jones
Nays:- None.
Absent:- None.

Attest:-

A. A. Moore.
Town Clerk.

J. E. Moore.
President of the Board of Trustees of the Town of San Anselmo.

The foregoing Ordinance hereby approved, this 9th day of August 1911.

President of the Board of Trustees of the Town of San Anselmo.

STATE OF CALIFORNIA, }
COUNTY OF SAN ANSELMO. } ss.

I, A. A. MOORE, Town Clerk of the Town of San Anselmo and ex-officio Clerk of the Board of Trustees of said Town, hereby certify that the foregoing is a full, true and correct copy of an ordinance regularly and duly passed at a regular monthly meeting of the Board of Trustees of said Town not less than five days after the date of its introduction.

That the said ordinance was numbered 88 and entitled Prescribing general rules and standard specifications for street and sidewalk work in the Town of San Anselmo.

That the said ordinance was thereafter duly posted in accordance with law and the order of said Board of Trustees in three conspicuous places in said town.

In witness, whereof, I have hereunto set my hand and placed the Corporate Seal of the Town of San Anselmo, at my office in said Town, this 12th day of August 1911.

A. A. Moore